

ARMOR-COAT

LOW VISOCSITY EPOXY HARD-COAT

Data Sheet Z-26

1. PRODUCT NAME

ARMOR-COAT
EPOXY BONDING AGENT

2. MANUFACTURER

Polygem, Inc.
1105 Carolina Drive
West Chicago, IL 60185
Telephone: (630) 231-5600
FAX: (630) 231-5604
Internet: www.polygem.com

3. PRODUCT DESCRIPTION

ARMOR-COAT is a 100% solids medium viscosity epoxy specially formulated for use as a bond agent that provides superior adhesion to new or existing surfaces. ARMOR-COAT is an easy to mix 1 to 1 by volume ratio supplied in clean and easy to use plastic pails.

ARMOR-COAT will bond to most concrete, wood, fiberglass and metal surfaces. ARMOR-COAT is resistant to moisture and most chemicals and solvents. ARMOR-COAT is also excellent for bonding and laminating or used as a filler/patching compound when mixed with our Thickening Agent .

Advantages

- LOW VISCOSITY
- NO VOC'S OR SOLVENTS
- SELF-LEVELING
- WON'T DISSOLVE BEADED FOAMS

Uses

For bonding new concrete to new or existing concrete or asphalt surfaces. ARMOR-COAT is ideal for use as a:

- SLIPFORM PAVING
- CONCRETE BONDING AGENT
- CRACK HEALING/SEALING
- EPOXY MORTARS AND GROUTS
- WATERPROOFING CONCRETE BLOCK
- HARD COAT FOR FOAM

4. APPLICATION INSTRUCTIONS

- 1) ARMOR-COAT can be applied by pouring, squeegee, brush, roller or spraying.
- 2) Clean surface by wiping with denatured alcohol or a non-petroleum based solvent.
- 3) Thoroughly mix measured amounts of 1 part of Part-A Resin with 1 part of Part-B Hardener by volume until streak free. Scrape side and bottom of pail frequently during mixing to insure a good mix. Mix only enough that can be applied in 30 minutes.

Packaging

ARMOR-COAT is available 2 Gal. Kits, 4 Gal. Kits and 10 Gal. Kits.

Color

Gray

Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for min. 24 months.

Limitations

- Not for use on contaminated or oily surfaces.
- Do not install when surface temperature is below 60°F (7°C) or above 85°F (32°C).
- During damp and/or cool conditions epoxy will cure slower and protect finished work from any contact until fully cured.

Cautions

- Wear chemical goggles and NIOSH approved respirator. Wear proper protective clothing and gloves to prevent direct contact of resins. Consult Material Safety Data Sheet for full listing protective requirements.
- ARMOR-COAT may irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin.
- For professional use only.
- Keep out of reach of children.

5. TECHNICAL DATA

Performance Properties
Test/Test Method Results

Pot Life @ 77°F (100 gms)	30 mins.
Thin Film Set-Time @ 77°F	2 hours
Cure time @ 77°F	2 days
Compressive ASTM D-695	11,500 psi (min)
Compressive Modulus	345,000 psi (min)
Tensile Strength ASTM D-638	8,150 psi (min)
Tensile Elongation ASTM D-638	2% (min)
Mix ratio by volume A/B	1:1
Mixed Viscosity	1,500 cps
Color Mixed	Gray

Polygem, Inc. warrants its products to be free of manufacturing defects and that, at the time and place of shipment, our material will meet current physical properties when applied within Polygem's directions and tested in accordance with ASTM and Polygem standards. Polygem, Inc.'s liability is limited to replacement of material found defective. As Polygem, Inc. has no control over the use to which others may put its products, it is recommended that the product be tested to determine if suitable for a specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Nothing contained herein shall be construed to be a recommendation to use or as a license to operate under or to infringe any existing patents.

1181 /Rev. 8/5/07

Data sheets are subject to change without notice, for latest revision check our website at www.polygem.com